

KEMKROME™ BASECOATS

Description

KemChrome™ is formulated with revolutionary new ultra-thin lamellar flakes that dry so flat they essentially form one large sheet with high brightness and reflectivity. Provided in a convenient ready to spray form these basecoats are easy to spray and handle. Great for that cool reflective look or a base for transparent topcoats like EyeKandy™. Must be applied over high gloss solvent resistant finishes for reflective effect.




Components

KK-01	Standard Reflective Chrome
KK-02	Deep Black Reflective Chrome
KK-03	White Chrome
KK-04	Polished Aluminum Effect



Suitable Substrates

KemChrome™ must be applied over high gloss solvent resistant finishes to achieve the reflective effect. Black basecoat followed by a high quality 2K clear is recommended. The clear must be polished to remove any surface imperfections prior to application of KemChrome™. The clear must be allowed to cure at least 24 hours at 75F prior to application of KemChrome.



Mix Ratio

KemChrome™ is provided ready to spray. Shake well then filter into your gun reservoir.



Application

Apply 2-3 light to medium coats using 50% overlap at a gun distance of 12-14 inches. Guns should be equipped with 0.9-1.4 mm tips and set for 30-40 PSI for conventional guns or 8-10 PSI at the cap for HVLP. Allow to flash 5-10 minutes between coats.

Allow to dry at least 12 hours then wipe gently with a soft lint free or micro fiber cloth to remove overspray and achieve best reflective effect.

When applying clear we recommend slight over-reduction of the clear and applying the 1st coat very lightly to minimize re-dissolving and lifting the chrome layer. Allow first coat to flash at least 15 minutes then apply medium wet coats of clear for flow. Fast drying clears work better to lock down the reflective flakes.

Read MSDS of all components before using. Use proper personal protective equipment at all times. For use by professionally trained painters. **KEEP OUT OF REACH OF CHILDREN.** Bayou Innovations, LLC warrants that its products are free from defects at time of shipping. All other warranties and guaranties of any kind whether expressed or implied are disclaimed.