

# KONFUSION™ COLOR CHANGE BASECOAT

## Description

KonFusion™ Color Change basecoats are a combination of highly weatherable urethane reactants, premium solvents, U.V. additives and the latest in Color Variable Pigment (CVP) technology. Our urethane basecoats spray easily, cover fast, lay down smooth, and dry quickly to a durable long lasting finish once properly clear coated. Unique technology changes between 2-5 hues depending on the angle you view them and lighting conditions. Apply over dark base (black gives most color change) for spectacular color shift without the jaw dropping price! Check local regulations for compliance before using.



## Components




<b>KF-01</b>	Nature's Fury	<b>KF-06</b>	Mountain Fall
<b>KF-02</b>	Storm Surge	<b>KF-07</b>	Hole Shot
<b>KF-03</b>	Ocean's Rip	<b>KF-08</b>	Tokyo Drift
<b>KF-04</b>	Tropical Storm	<b>KF-09</b>	Psychotic Illusions
<b>KF-05</b>	Toxic Tide	<b>KF-10</b>	Nuclear Gold

## Suitable Substrates



Apply over 2K urethane primer or basecoat after proper flash times. Not recommended for direct use over epoxy or enamel primers. For best color change apply over dark bases such as our SGCB00 BlackOut Black Base. Other colors may be used to give varying color shift effects.

## Mix Ratio



For spray applications mix 2 parts KonFusion base with 1 part UR series urethane grade thinner by volume. Additional reduction may be required for use in an air brush application. Mix gently then strain before use. Four ounce sizes come ready to spray. Just shake and shoot! For use with PreVal Aerosol Guns: Mix 1 part KonFusion Color with 1 part UR Series Thinner by volume then add to glass application jar.

## Application



Apply 3-5 medium coats using 75% overlap at a gun distance of 6-8 inches. HVLP or reduced pressure (RP) guns should be equipped with 1.2-1.5 mm tips and generally set for 24-32 psi standard HVLP or 12-18 psi for RP guns. Avoid heavy or very light coats so as to ensure good orientation. When painting sides of vehicles walk the entire length of the vehicle spraying before then overlap 75% of your previous spray and spraying all the way back down the to the other end of the vehicle side. Do not paint one quarter panel at a time to avoid light streaks where you overlap. Allow to flash dull between coats. After final coat application allow to flash at least 30 minutes but no more than 24 hours before application of a 2K polyurethane clear. Always prepare a test panel to verify gun settings, effect, and desired color before painting your object.