



UC-410 MS 2K Polyurethane Clearcoat

Description

UC-410 is a two component polyurethane clearcoat designed for ease of application, good flow and leveling, quick dry times, and easy polishability. Fortified with U.V. additives this product is built to last! Apply over automotive grade basecoats such as KemBase products including KonFusion color changes and EyeKandy kandy finishes. Can be used for application of KemFx pearls and powders when mixed properly. When properly mixed this product contains isocyanates and as such great care should be taken in handling a personal protection



Components




- **UC-410** **2K MS Polyurethane Clear**
- **UA-040, 41, 42** **UreKem Topcoat Activators (Fast, Standard, Slow)**
- **UR-010, 011, 012** **UR Series Urethane Reducers (Optional)**
- **ABS-10, ARE-66, AFE-52, AUC-56, AFP-01 (Optional Additives)**



Suitable Substrates

Apply over properly flashed automotive basecoats, or cured properly prepared 2K automotive paint surfaces (sanded 600 grit then cleaned).



Mix Ratio

For spray applications mix 4 parts UC-410 with 1 part UA-040, 041, or 042 urethane topcoat activator by volume. Gently mix then filter through a fine paint filter into your spray gun. Additional reduction may be required for use in an air brush application. This product has a 3-4 pot life so mix only enough that can be used within that time period.



Application

Apply 2-3 medium wet to wet coats using 50% overlap at a gun distance of 6-10 inches. Guns should be equipped with 1.2-1.5 mm tips and set for 40-55 PSI for conventional guns or 8-10 PSI at the cap for HVLP. Allow to flash 10-15 minutes between coats.



Cleaning

Clean equipment immediately after use with locally compliant cleaning solvent. Dispose of all waste according to local regulations.

Read MSDS of all components before using. Use proper personal protective equipment at all times. For use by professionally trained painters. **KEEP OUT OF REACH OF CHILDREN.** Bayou Innovations, LLC warrants that its products are free from defects at time of shipping. All other warranties and guaranties of any kind whether expressed or implied are disclaimed.